

## Technical Information

**Polymer ST 61****For high quality wood floor adhesives with high strength and elasticity****Applications**

Polymer ST 61 is a high quality polymer which is used for wood floor adhesive formulations.

Polymer ST 61 allows a high degree of flexibility for the formulations: adhesives with high strength and hardness are possible as well as soft adhesives with high elasticity.

**Example I:**

Tensile strength 1.65 N/mm<sup>2</sup>  
Elongation 140 %, Shore A 53

**Example II:**

Tensile strength 4.4 N/mm<sup>2</sup>  
Elongation 80 %, Shore A 73

**Technical properties (no specification data)**

|                                  |                         |
|----------------------------------|-------------------------|
| Appearance                       | colourless, transparent |
| Viscosity                        | approx. 35 000 mPas     |
| Plasticizer                      | none                    |
| Tensile strength in formulation* | 1–5 N/mm <sup>2</sup>   |
| Elongation in formulation*       | 80 – 230 %              |
| Shore A in formulation*          | 30 – 70                 |

\*formulation available upon request



## Benefits

Polymer ST 61 is a silane-terminated polymer for formulations which meet the demands of ecolabels such as “Blauer Engel” or “Ecodecode EC1”.

The mechanical performance of Polymer ST 61 allows high dosages of fillers without compromising the tensile strength of the formulation.

## Processing

When selecting raw materials, especially when it comes to fillers (e.g. CaCO<sub>3</sub>), it is recommended to use products with the lowest water content possible. Fillers can be pre-dried before use.

Containers should be stored at a similar temperature to their surroundings as to reduce the chance for water condensation. This is of particular importance when materials are stored outside in the winter months.

It is necessary to keep all equipment used for processing clean and dry. Surfaces can be cleaned with volatile solvents, such as acetone, if necessary.

The product is activated for reaction once the catalyst is added or when exposed to moisture. After this time it must be kept in closed, dry containers.

## Packaging

950 kg IBC

## Shelf life

12 months when stored in closed containers at temperatures up to 104 °F (40 °C).

## Registration status

The ingredients of Polymer ST 61 are listed in the following chemical inventories:

EINECS/ELINCS, TSCA, DSL, PICCS, TCSI

Further information is available on request.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Evonik Nutrition & Care GmbH**  
Charlottenburger Straße 9  
21502 Geesthacht, Germany  
Phone +49 4152 8092-0  
Fax. +49 4152 79156  
[www.evonik.com/interface-performance](http://www.evonik.com/interface-performance)  
[interface-performance@evonik.com](mailto:interface-performance@evonik.com)

